

# IXOLAR<sup>™</sup> High Efficiency Solar Cells

## Description

IXOLAR<sup>™</sup> Solar Cells are IXYS' monocrystalline, high efficiency solar cell technology products incorporating an enhanced light trapping surface. There are 7 different cell sizes available: 36mm<sup>2</sup>, 120mm<sup>2</sup>, 240mm<sup>2</sup>, 342mm<sup>2</sup>, 360mm<sup>2</sup>, 480mm<sup>2</sup> and 676mm<sup>2</sup>.

The IXOLAR<sup>™</sup> Solar Cells are ideal for charging various battery powered and handheld consumer products such as mobile phones, cameras, PDAs, MP3 players and toys. They are also suitable for industrial applications such as wireless sensors, portable instrumentation and for charging emergency backup batteries.

With an efficiency of typically 17%, these solar cells give the ability to extend run time even in "low light" conditions and increase battery life and run time in a small footprint, which can be easily accommodated in the design of Portable Products.

IXOLAR<sup>™</sup> products have a very good response over a wide wavelength range and therefore can be used in both indoor and outdoor applications.

Part Number	X [mm]	Y [mm]		Short Circuit Current [mA]	Peak Power [mW]
XOD17-04B	6	6	630	12	6
XOD17-12B	6	20	630	42	20
XOD17-24B <sup>*1)</sup>	12	20	630	84	40
XOD17-34B	18.5	18.5	630	120	56
XOD17-36B <sup>*1)</sup>	18	20	630	126	60
XOD17-48B <sup>*1)</sup>	24	20	630	168	80
XOD17-68B	26	26	630	236	112

B-suffix: wire-bondable front-side metallization (non solderable)

<sup>\*1)</sup> do not use with new designs

#### **Electrical Characteristics**

V <sub>oc</sub> open	circuit voltage	630	mV
J <sub>sc</sub> short	circuit current density	35	mA/cm <sup>2</sup>
V <sub>mpp</sub> voltag	e at max. power point	505	mV
J <sub>mpp</sub> currer	t density at max. power point	32.5	mA/cm <sup>2</sup>
P <sub>mpp</sub> maxin	num peak power	16.6	mW/cm <sup>2</sup>
FF fill fac	tor	> 75	%
<b>n</b> efficie	ncy	17	%
ΔV <sub>oc</sub> /ΔT open	circuit voltage temp. coefficient	-2.1	mV/K
ΔJ <sub>sc</sub> /ΔT short	circuit current temp. coefficient	0.12	mA/(cm²K)
t cell th	ickness	250	μm

<sup>\*2)</sup> All values measured at Standard Condition: 1 sun (= 100mW/cm<sup>2</sup>), Air Mass 1.5, 25°C

Operating temperature range: -40°C .... + 85°C

XOD17 solar cell dies are RoHS compliant

#### IXYS reserves the right to change limits, test conditions and dimensions

IXYS Semiconductor GmbH Edisonstr. 15, D-68623 Lampertheim (Germany) Phone +49-6206-503-0, Fax +49-6206-503-627 1-2



Back-side contact (+)

#### **Features**

- Monocrystalline silicon technology
- High efficiency
- Enhanced light trapping surface

### Applications

- Battery chargers for portables such as cell phones, PDAs, GPS-Systems, ...
- "Green" electricity generation
- Power backup for UPS, Sensors, Wearables

#### Advantages

- · Long life and stable output
- Solderable back-side metallization
- Bondable front-side metallization
- Available in die and wafer form

#### © 2005 IXYS All rights reserved

IXYS Corporation 1590 Buckeye Drive, Milpitas, CA 95035-7418 Phone 408-457-9000, Fax 408-496-0670



# XOD17

## **Typical Performance Data**



Short-Circuit Current Density vs. Temperature



**Open-Circuit Voltage vs. Irradiance** 



IXYS reserves the right to change limits, test conditions and dimensions

IXYS Semiconductor GmbH Edisonstr. 15, D-68623 Lampertheim (Germany) Phone +49-6206-503-0, Fax +49-6206-503-627

Rev. Mar. 2008

**Open-Circuit Voltage vs. Temperature** 



#### **External Quantum Efficiency**



© 2005 IXYS All rights reserved

IXYS Corporation 1590 Buckeye Drive, Milpitas, CA 95035-7418 Phone 408-457-9000, Fax 408-496-0670