

Sep, 1st, 2014

RE: LFPCN41220

To: Our Valued Customers.

From: Littelfuse Product Management Team

Subject: Littelfuse DO-214AC Package Process Upgrade - matrix lead-frame design

Similar to LFPCN41196 issued last year in which Littelfuse migrated DO-214AB package from single strip design to matrix lead frame design (Automation Structure), This PCN is to upgrade another package DO-214AC to be matrix lead-frame design.

This new matrix design in DO-214AC packages will allow Littelfuse to align the same matrix structure design using among full DO-214AC series products, existing DO-214AA as well as DO-214AB products.

The matrix lead frame structure design will contribute great improvement in terms of automation, quality, productivity increasing as well as capacity expansion

The scope of change will cover full DO-214AC packages from Semiconductor Business Unit (SBU) products including SIDACTor® devices, SIDAC and Commodity TVS, Please refer to attachment for details and affected PNs.

There are no changes to fit, form, and function of the finished product. Qualification efforts are completed. Please see the attached documentation All affected products have been fully qualified in accordance with established performance and reliability criteria. The attached pages summarize the qualification results. Full qualification data and/or samples will be available upon request.

Form, Fit, Function Changes: None Part Number Changes: None Effective Date: Dec, 1<sup>st</sup>, 2014 Replacement Products: N/A Last Time Buy: N/A

If you have any other question or concerns, please contact Littelfuse® local sales representative, or Meng Wang, Assistant Product Manager for further assistance.

We highly value your business and look forward to assisting you whenever possible.

Best Regards,

Meng Wang

Assistant Product Manager Commodity TVS and SIDACTor Tel: +86 510 85277701 ext – 7955 Mwang3@littelfuse.com Jia Zhu

Assistant Product Manager SIDAC Tel : +86 510 85277701 Ext -7966 jzhu3@littelfuse.com



800 E. Northwest Highway Des Plaines, IL 60016

Product/Process Change Notice (PCN)					
PCN#: LFPCN41220 Date: Sep 1 <sup>st</sup> 2	014	Contact Information			
Product Identification:		Name: Meng Wang			
DO-214AC Package Products		Title: Assistant Product Manager			
Implementation Date for Change:		Phone #: +86 510 85277701- 7955			
Dec 1 <sup>st</sup> 2014		Fax#: +86 510 85277700			
		E-mail: Mwang3@littelfuse.com			
Category of Change:	Descrip	otion of Change:			
Assembly Process	Throug	h this PCN after upgrading DO-214AC to Matrix Lead frame design.			
Data Sheet	Littelfu	se upgraded all DO-214 package products among Semiconductor			
Technology	Busines	ss Unit (SBU) surface mount type to matrix lead frame design , which is			
Discontinuance/Obsolescence		fficient, better product repeatiblity, and better uniform through			
Equipment		ation, thus Littelfuse can deliver more reliable device to customer.			
Raw Material	1	e will be give to implement this we use do in Dec. ( <sup>St</sup> 2014) and followed			
_		se will begin to implement this upgrade in Dec 1 <sup>st</sup> 2014 and followed			
Fabrication Process	•	ions period and will be fully Matrix lead frame structure			
Other:	by June	9 30 <sup>th</sup> 2015			
Important Dates:					
Qualification Samples Available: Sep	1 <sup>th</sup> 2014	4 🗌 Last Time Buy: N/A			
Final Qualification Data Available: Se	p 1 <sup>th</sup> 2	014			
Date of Final Product Shipment: N/A					
Method of Distinguishing Changed Pro	duct				
Product Mark, N/A					
Date Code, 4Lxxx					
Other,					
Demonstrated or Anticipated Impact or	n Form,	Fit, Function or Reliability:			
N/A					
LF Qualification Plan/Results:					
availabe on Sep 1 <sup>th</sup> 2014, see attached ne	ext page				
Customer Acknowledgement of Receip	t: Littelfu	use requests you acknowledge receipt of this PCN. In your acknowledgement, you can			
grant approval or request additional information. Litt	telfuse wil	assume the change is acceptable if no acknowledgement is received within 30 days			
of this notice. Lack of any additional response within 90 days of PCN issuance further constitutes acceptance of the change.					

Littelfuse, WX East 1# Zhen Fa 6 Road Shuo Fang Industrial Park Wuxi, Jiangsu 214142

## **Product Qualification Report**

To: Those who may concern

From: Product Engineering, Littelfuse, WX

Date: Aug. 27, 2014 - Rev 0.0

Subject: Qualification Report for Littelfuse TVS/SIDACtor/SIDAC DO-214AC Matrix lead frame Structure

#### **Purpose:**

This report is to inform the successful LF Commodity TVS/SIDACtor/SIDAC DO-214AC Matrix lead frame Structure qualification test results

#### **Change demonstration**





1. Double lead frames:

Top lead frame is same as bottom lead frame as below:





1. Matrix lead frame + Clip



Product Package	Product Series	Representative Test Sample Part Numbers		
		SMAJ70CA		
		SMAJ300A		
DO-214AC	TVS	P4SMA300A		
		SMAJ300CA		
		SMAJ5.0A		
	SIDACtor	P833P0080S1BLRP		
	SIDACIO	P3100S1BLRP		
	SIDAC	K2000S1URP		

# 1. Qualification Types (Test Vehicle)

## 2. Qualification Test Items and Result Summary:

## SIDACTor

Test Category Description		Sample P/N	Sample Qty	Littelfuse test Ref#	Contents/Conditions	Result Summary	
	Electrical	P833P0080S1BLRP	30	60506	Vво. Vdrm , IH, VT	100% meet published spec.	
	Parameters	P3100S1BLRP	30	60514			
	surge out 8*20us	P833P0080S1BLRP	10	60506	+/- hit, from rated lpp, 0.1lpp	100% passing at Rated	
Parametric	surge out 8 200s	P3100S1BLRP	10	60514	step	IPP	
Falametric	surge out 10*700us	P833P0080S1BLRP	10	60506	+/- hit, from rated lpp, 0.1lpp	100% passing at Rated	
	surge out 10 700us	P3100S1BLRP	10	60514	step	IPP	
	surge out 10*1000us	P833P0080S1BLRP	10	60506	+/- hit, from rated lpp, 0.1lpp	100% passing at Rated	
	surge out to tooous	P3100S1BLRP	10	60514	step	IPP	
	Pre-condition	P833P0080S1BLRP	120	60503	SMD qualification parts for	Follow JESD22-A113D	
	Fie-condition	P3100S1BLRP	120	60510	TC,AC,H3TRB	FOILOW JESDZZ-ATT3D	
	DC/AC Blocking (HTRB)	P833P0080S1BLRP	77	60503	125°C, 24h at +/-80%Vdrm, AC blocking test with AC peak 80%	0 failure at 1008h	
		P3100S1BLRP	77	60510	Vdrm 168/504/1008h		
	HTSL	P833P0080S1BLRP	40	60503	168/504/1008h at 150°C	0 failure at 1008h	
		P3100S1BLRP	40	60510	+preconditioning		
	Temp Cycle	P833P0080S1BLRP	40	60503	100000000000000000000000000000000000000	0 failure	
Reliability		P3100S1BLRP	40	60510	100cycles, -65°C & +150°C,		
Tendonity	(H3TRB)	P833P0080S1BLRP	40	60503	168/504/1008 hours at Tj = 85C/85% RH with device reverse	0 failure at 1008h	
		P3100S1BLRP	40	60510	biased at 80% VDRM and not exceed 52V.		
	Autoclave	P833P0080S1BLRP	40	60503	TA 101%C DLL 100% 48/065	Pass	
		P3100S1BLRP	40	60510	TA = 121°C, RH =100% 48/96h		
	1401	P833P0080S1BLRP	10	60503		Pass	
	MSL	P3100S1BLRP	10	60510	Per JEDEC-J-STD-020C, Level1		
		P833P0080S1BLRP	30	60503	260℃, 10 seconds*3 full		
	RSH	P3100S1BLRP	30	60510	submerge	0% failure after RSH	

Test Category	Description	Sample P/N	Sample Qty	Littelfuse test Ref#	Contents/Conditions	Result Summary
		SMAJ70CA	600	60500		
		SMAJ300A	600	60516	7	
		P4SMA300A	600	60538	7	
Parametri	ſ	SMAJ300CA	600	60546		100% meet published
C	Electrical Parameters	SMAJ5.0A	600	60661	Vbr, Ir	spec.
		SMAJ70CA	600	60500		·
		SMAJ300A	600	60516	1	
	F	P4SMA300A	600	60538		
Surge IPP	F	SMAJ300CA	600	60546		100% passing at
test	10X1000us Surge Test	SMAJ5.0A	600	60661	+/- 1 hit, at rated IPP	Rated IPP
	ŭ	SMAJ70CA	231	60500		
	ľ	SMAJ300A	231	60516	-	
		P4SMA300A	231	60538	CMD swellfestion	
	ľ	SMAJ300CA	231	60546	SMD qualification parts for	Follow JESD22-
	Pre-condition (PC)	SMAJ5.0A	231	60661	TC,AC,H3TRB	A113D, 0 failure
		SMAJ70CA	77	60500		
		SMAJ300A	77	60516	-	
	F	P4SMA300A	77	60538	-	
	-	SMAJ300CA	77	60546	150℃, DC bias=100%	Follow JESD22-A108,
	DC Blocking (HTRB)	SMAJ5.0A	77	60661	of Vr spec	0 failure at 1008hrs
	2 0 2.000g (2)	SMAJ70CA	77	60500		
	-	SMAJ300A	77	60516	-	
	F	P4SMA300A	77	60538	-	
	High Temp Storage	SMAJ300CA	77	60546	-	Follow JESD22-A103,
	(HTSL)	SMAJ5.0A	77	60661		0 failure at 1008hrs
	(1102)	SMAJ70CA	77	60500		
	ŀ	SMAJ300A	77	60516	-	
	ŀ	P4SMA300A	77	60538	-	
	Biased Temp &	SMAJ300CA	77	60546		Follow JESD22-A101,
	Humidity (H3TRB)	SMAJ5.0A	77	60661	85℃, 85%,RH DC bias=100% of VR spec	,
		SMAJ70CA	77	60500		
	-	SMAJ300A	77	60516	-	
		P4SMA300A	77	60538	1	
		SMAJ300CA	77	60546	EE*** 9 1E0*** (-:- +-	
	Temp Cycle	SMAJ5.0A	77	60661	55℃&150℃ (air to air)	Follow JESD22-A104, 0 failure at 1000cycles
		SMAJ70CA	77	60500		
		SMAJ300A	77	60516	1	
		P4SMA300A	77	60538	1	
Daliahilit		SMAJ300CA	77	60546	- T. 404% DU	
Reliability Test	Autoclave	SMAJ5.0A	77	60661	T <sub>A</sub> = 121℃, RH =100%, 15psig	Follow JESD22-A102, 0 failure at 96hrs
1001		SMAJ70CA	77	60500		0 1011010 01 301115
		SMAJ300A SMAJ300A	77	60516	1	
		P4SMA300A	77	60538	-	
		SMAJ300CA	77	60546		
<b>.</b>	MOL	SMAJ5.0A	77	60661	Follow JEDEC J-STD-	Deep
Reliability	MSL				020D, MSL 1	Pass Follow IESD22 B106
Test	RSH	SMAJ70CA	77	60500	260℃, 10 seconds	Follow JESD22-B106

#### SIDAC:

Test Category	Description	Sample P/N	Sample Qty	Littelfuse test Ref#	Contents/Conditions Standard		Result Summary
	Electrical	K2000S1URP	362	60506	Vво. Vdrm , IH, VT		100% meet published
Parametric	ITRM	K2000S1URP	10	60506	TA 125°C, 168hr, ITRM = 160A+10/-0Apeak, 5Hz, 10usec Pulse width		pass
	ITSM	K2000S1URP	5	62164	50hz, Single cycle test from rated lpp, 0.1lpp step		100% passing at Rated IPP
	Pre-condition	K2000S1URP	120	60506	SMD qualification parts for TC,AC,H3TRB	JESD22-A113D	pass
	AC Blocking (HTRB)	K2000S1URP	77	60506	125°C, Vpk=Vdrm 168/504/1008h	JESD22- A108	0 failure at 1008h
Reliability	HTSL	K2000S1URP	40	60506	168/504/1008h at 150°C	JESD22-A103	0 failure at 1008h
Reliability	Temp Cycle	K2000S1URP	40	60506	100cycles, -40°C & +150°C, dwell time 15mins, transfer time less than 10sec	JESD22-A104	0 failure
	H3TRB	K2000S1URP	40	60506	H3TRB, 85°C, 85%RH, +DC at 80%VBO min, 1,008hr	JESD22-A101	0 failure at 1008h
	RSH	K2000S1URP	30	60506	No preheating Bath 260°C, full submerge 10 sec x 2 time	JESD22- B106	0% failure after RSH

### 3. MTBF Calculation

Estimate of Failure Rate, MTBF, FITS for a Given Operation Temperature (See note)

Temp ℃	% FR/khrs	MTBF (K)	FITS
30	0.000455821	2193844	0.46
60	0.014313827	69863	14.31
80	<b>80</b> 0.102905353		102.91
100	<b>100</b> 0.59881152		598.81
<b>125</b> 4.21988859		237	4219.89
150	23.61087256	42	23610.87

Note: The Mean-Time-Between-Failure (MTBF) in hours and the percent failure rate per 1000 hours (%FR/khr) are computed at a 60% confidence level using the chi square method and the Arrhenius derating model for various junction operating temperatures. For the calculations, a value of 1 eV was used for the activation energy.

### 4. Conclusion

According to the above qualification test results, Littelfuse concluded that TVS/SIDACtor/SIDAC DO-214AC Matrix lead frame structure have passed Qualification test at WTC Lab, which is approved to release for mass production.