PCN Number:		20	0160	720001A					P	CN Date:	08/02/2016	
Titl	e:	Qualify ASES	SH a	ıs ar	additional	Assemb	ly & Test si	te 1	for	select d	evices	
Cus	stome	er Contact:	PC	N Ma	nager	Dept:	Quality S	erv	/ice			
	Change Type:						<u> </u>					
$\boxtimes$		mbly Site			Assembly	Process				Assem	bly Materia	ls
	Desi				Electrical S		tion				nical Specif	
$\boxtimes$	Test	Site		$\boxtimes$	Packing/S	hipping/	Labeling			Test P	rocess	
	Wafe	er Bump Site			Wafer Bun	np Mate	rial			Wafer	<b>Bump Proc</b>	ess
	Wafe	er Fab Site			Wafer Fab					Wafer	Fab Proces	S
					Part numb							
						PCN D	<u>etails</u>					
		ion of Chang										
		A is to remov										
nıgı	niignt	ed in yellow. <sup>-</sup>	ines	se a	evices were	inadver	tently adde	a a	ana	not arre	ected by thi	s cnange.
Tov	ac Ind	strumonto io r	مامما	d	-0 20001100	o tha au	olification o	fΛ	CE	CU 26 21	a additional	Accombly 9
		struments is p for the list of										
165	t Site	ioi the list of	uev	ices	SHOWIT DEIC	JW. Mau	eriai uillere	HC	25 L	Jetween	i sites as io	nows.
	Asse	mbly Site	Ass	sem	bly Site Or	igin A	ssembly C	ou	ntr	y Code	Assem	bly City
	TI	Malaysia			MLA		N	1Y			Kuala Lumpur	
	<i></i>	SESH			ASH		C	N			Sha	nghai
_						<u> </u>						3
Mat	terial	Differences	:									
				Т	I Malaysia	1	ASES	Н				
ı	Mount	Compound	4042500				EY1000	06	3			
	Mold	compound			4206193		EN2000	50	7			
	Le	ad finish	NiPdAu				Matte Sn					
<u>nur</u> ava	Upon expiration of this PCN, TI will combine lead free solutions in a single <u>standard part</u> <u>number</u> , for example; <u>MAX3221CPWR</u> – can ship with both Matte Sn and NiPdAu. When available customers may specify NiPdAu finish by ordering the part with the G4 suffix, e.g. <b>MAX3221CPWRG4</b> ."											
	t cove : MQ.	erage, insertio	ns,	con	ditions will ı	remain c	onsistent v	/ith	cu	ırrent te	sting and v	erified with
		for Change:										
Cor	ntinuit	y of Supply										
Ant	Anticipated impact on Fit, Form, Function, Quality or Reliability (positive / negative):											
Nor	None											
Ant	ticipa	ted impact o	on N	1ate	rial Declar	ration						
	No Impact to the Material Declaration    Material Declaration    Material Declaration    Material Declaration    Material Declaration    Product Content reports are driven from production data and will be available following the production release. Upon production release the revised reports can be obtained from the TI ECO website.				oduction							

### Changes to product identification resulting from this PCN:

Assembly Site		
TI Malaysia	Assembly Site Origin (22L)	ASO: MLA
ASESH	Assembly Site Origin (22L)	ASO: ASH

Sample product shipping label (not actual product label)



(1P) \$N74L\$07N\$R (Q) 2000 (D) 0336 (31T)LOT: 3959047MLA (4W) TKY(1T) 7523483812 (P) 0033317

(2P) REV: (V) 0033317 (20L) CSO: SHE (21L) CCO:USA (22L) ASO: MLA (23L) ACO: MYS

LBL: 5A (L)TO:3750

### **Topside Device marking:**

Assembly site code for MLA= K

Assembly site code for ASH = A

#### **Product Affected**

MAX3221CPW	MAX3221ECPWG4	MAX3221IPW	TRS3221ECPWR-LI
MAX3221CPWE4	MAX3221ECPWR	MAX3221IPWG4	TRS3221EIPW
MAX3221CPWG4	MAX3221EIPW	MAX3221IPWR	TRS3221EIPWR
MAX3221CPWR	MAX3221EIPWE4	MAX3221IPWRG4	TRS3221EIPWRG4
MAX3221CPWRE4	MAX3221EIPWG4	TRS3221CPWR	TRS3221IPW
MAX3221CPWRG4	MAX3221EIPWR	TRS3221CPWRG4	TRS3221IPWR
MAX3221ECPW	MAX3221EIPWRE4	TRS3221ECPW	
MAX3221ECPWE4	MAX3221EIPWRG4	TRS3221ECPWR	

# Qualification Report Multisource MAX3221ECPWR and MAX3221CPWR to ASESH Approve Date 01-Jul-2016

### **Product Attributes**

Attributes	Qual Device: MAX3221CPWR	Qual Device: MAX3221ECPWR	QBS Product Reference: TRS3243CDB	QBS Process Reference: MAX232ECDW	QBS Process Reference: MAX3237EDW
Assembly Site	ASESH	ASESH	MLA	MLA	MLA
Package Family	TSSOP	TSSOP	SSOP	SOIC	SOIC
Flammability Rating	UL 94 V0	UL 94 V0	UL 94 V0	UL 94 V-0	UL 94 V-0
Wafer Fab Supplier	DFAB	DFAB	DFAB	DFAB	DFAB
Wafer Process	LBC3S	LBC3S	LBC3S	LBC3S	LBC3S

Attributes	QBS Process Reference: SN75C3238EDW	QBS Package Reference: SN74LV14APWR	QBS Package Reference: SN74LVC14APWR	QBS Package Reference: ULN2003APW
Assembly Site	TAI	ASESH	ASE-SH	ASESH
Package Family	SOIC	TSSOP	TSSOP	TSSOP
Flammability Rating	UL 94 V-0	UL 94 V-0	UL 94 V-0	UL 94 V-0
Wafer Fab Supplier	DFAB	SFAB	FFAB	SFAB
Wafer Process	LBC3S	EPIC1-S	P9750	JI

<sup>-</sup> QBS: Qual By Similarity

## **Qualification Results**

Data Displayed as: Number of lots / Total sample size / Total failed

Туре	Test Name / Condition	Duration	Qual Device: MAX3221CPWR	Qual Device: MAX3221ECP WR	QBS Product Reference: TRS3243CDB	QBS Process Reference: MAX232ECD W
AC	Autoclave 121C	96 Hours	-	-	-	-
ED	Electrical Characterization	Per Datasheet Parameters	-	-	Pass	Pass
HAST	Biased HAST, 130C/85%RH	96 Hours	-	-	-	-
ESD	ESD - IEC Air Gap	15000 V	-	-	-	1/3/0
HBM	ESD - HBM	4000 V	1/3/0	1/3/0	-	-
HBM	ESD - HBM -HIGH	15000 V	-	-	1/3/0	1/3/0
CDM	ESD - CDM	1500 V	1/3/0	1/3/0	-	1/3/0
HTOL	Life Test, 150C	300 Hours	-	-	1/77/0	-
HTSL	High Temp. Storage Bake, 150C	1000 Hours	-	-	-	-
LU	Latch-up	(per JESD78)	1/6/0	1/6/0	1/6/0	3/9/0
TC	Temperature Cycle, -65C/150C	500 Cycles	-	-	-	-
ТНВ	Biased Temperature and Humidity, 85C/85%RH	1000 Hours	-	-	-	-
UHAST	Unbiased HAST 130C/85%RH	96 Hours	-	-	-	-
WBP	Bond Strength	Wires	-	-	-	-

Туре	Test Name / Condition	Duration	QBS Process Reference: MAX3237E DW	QBS Process Reference: SN75C3238 EDW	QBS Package Reference: SN74LV14 APWR	QBS Package Reference: SN74LVC14A PWR	QBS Package Reference: ULN2003AP W
AC	Autoclave 121C	96 Hours	1/77/0	1/77/0	-	-	-
ED	Electrical Characterization	Per Datasheet Parameters	-	-	Pass	Pass	Pass
HAST	Biased HAST, 130C/85%RH	96 Hours	-	-	1/77/0	1/77/0	1/77/0

<sup>-</sup> Qual Devices qualified at LEVEL1-260CG: MAX3221CPWR, MAX3221ECPWR

<sup>-</sup> Device MAX3221ECPWR contains multiple dies.

ESD	ESD - IEC Air Gap	15000 V	-	-	-	-	-
НВМ	ESD - HBM	4000 V	-	-	-	-	-
НВМ	ESD - HBM -HIGH	15000 V	-	-	-	-	-
CDM	ESD - CDM	1500 V	-	-	-	-	-
HTOL	Life Test, 150C	300 Hours	1/40/0	1/40/0	1/77/0	1/77/0	1/77/0
HTSL	High Temp. Storage Bake, 150C	1000 Hours	1/77/0	1/77/0	1/77/0	1/77/0	1/77/0
LU	Latch-up	(per JESD78)	-	-	-	-	-
TC	Temperature Cycle, - 65C/150C	500 Cycles	1/77/0	1/77/0	1/77/0	1/77/0	1/77/0
ТНВ	Biased Temperature and Humidity, 85C/85%RH	1000 Hours	1/26/0	1/26/0	-	-	-
UHAST	Unbiased HAST 130C/85%RH	96 Hours	-	-	1/77/0	1/77/0	1/77/0
WBP	Bond Strength	Wires	-	-	1/76/0	1/76/0	1/76/0

<sup>-</sup> Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

### Green/Pb-free Status:

Qualified Pb-Free(SMT) and Green

For questions regarding this notice, e-mails can be sent to the regional contacts shown below or your local Field Sales Representative.

Location	E-Mail
USA	PCNAmericasContact@list.ti.com
Europe	PCNEuropeContact@list.ti.com
Asia Pacific	PCNAsiaContact@list.ti.com
Japan	PCNJapanContact@list.ti.com

<sup>-</sup> The following are equivalent HTOL options based on an activation energy of 0.7eV: 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

<sup>-</sup> The following are equivalent HTSL options based on an activation energy of 0.7eV: 150C/1k Hours, and 170C/420 Hours

<sup>-</sup> The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles Quality and Environmental data is available at Tl's external Web site: http://www.ti.com/